

PRODUCT DATA SHEET

AMBERLITE™ IRI20 H
Industrial Grade Strong Acid Cation Exchanger

AMBERLITE IRI20 H resin is a gel type strongly acidic cation exchange resin of the sulfonated polystyrene type. It is used for water demineralisation (in H⁺ form) in co-flow regenerated units.

AMBERLITE IRI20 H resin is an excellent general purpose cation exchange resin that can be used for a wide variety of water demineralisation applications.

PROPERTIES

Physical form _____	Amber spherical beads
Matrix _____	Styrene divinylbenzene copolymer
Functional group _____	Sulfonic acid
Ionic form as shipped _____	H ⁺
Total exchange capacity ^[1] _____	≥ 1.80 eq/L (H ⁺ form)
Moisture holding capacity ^[1] _____	53 to 58 % (H ⁺ form)
Shipping weight _____	800 g/L
Particle size	
Uniformity coefficient ^[1] _____	≤ 1.8
Harmonic mean size ^[1] _____	0.620 to 0.830 mm
< 0.300 mm ^[1] _____	2 % max
Maximum reversible swelling _____	Na ⁺ → H ⁺ ≤ 11 %

^[1] Contractual value
 Test methods available upon request.

SUGGESTED OPERATING CONDITIONS

Maximum operating temperature _____	135 °C
Minimum bed depth _____	700 mm
Service flow rate _____	5 to 40 BV*/h
Regeneration	
Regenerants _____	HCl H ₂ SO ₄
Level (g/L) _____	50 to 150 60 to 240
Concentration (%) _____	5 to 8 0.7 to 6
Minimum contact time _____	30 minutes
Slow rinse _____	2 BV at regeneration flow rate
Fast rinse _____	2 to 4 BV at service flow rate

* 1 BV (Bed Volume) = 1 m³ solution per m³ resin

PERFORMANCE

The operating capacity depends on several factors such as the water analysis and the level of regeneration. The data to calculate the operating capacity and the ionic leakage with co-flow regeneration are given in the Engineering Data Sheets: EDS 0264 A and EDS 0265 A.



LIMITS OF USE

AMBERLITE IR120 H resin is suitable for industrial uses. For other specific applications such as pharmaceutical, food processing or potable water applications, it is recommended that all potential

users seek advice from Rohm and Haas in order to determine the best resin choice and optimum operating conditions.

HYDRAULIC CHARACTERISTICS

Figure 1 shows the bed expansion of AMBERLITE IR120 H resin as a function of backwash flow rate and water temperature. Figure 2 shows the pressure drop data for AMBERLITE IR120 H resin, as a function of service flow rate and water temperature. Pressure drop data are valid at the start of the service run with clear water and a correctly classified bed.



All our products are produced in ISO 9001 certified manufacturing facilities.

Rohm and Haas/Ion Exchange Resins - Philadelphia, PA - Tel. (800) RH AMBER - Fax: (215) 409-4534
Rohm and Haas/Ion Exchange Resins - 75579 Paris Cedex 12 - Tel. (33) 1 40 02 50 00 - Fax : 1 43 45 28 19

<http://www.amberlite.com>

ROHM AND HAAS 

AMBERLITE is a trademark of Rohm and Haas Company and its affiliates, Philadelphia, U.S.A.

Ion exchange resins and polymeric adsorbents, as produced, contain by-products resulting from the manufacturing process. The user must determine the extent to which organic by-products must be removed for any particular use and establish techniques to assure that the appropriate level of purity is achieved for that use. The user must ensure compliance with all prudent safety standards and regulatory requirements governing the application. Except where specifically otherwise stated, Rohm and Haas Company does not recommend its ion exchange resins or polymeric adsorbents, as supplied, as being suitable or appropriately pure for any particular use. Consult your Rohm and Haas technical representative for further information. Acidic and basic regenerant solutions are corrosive and should be handled in a manner that will prevent eye and skin contact. Nitric acid and other strong oxidising agents can cause explosive type reactions when mixed with Ion Exchange resins. Proper design of process equipment to prevent rapid buildup of pressure is necessary if use of an oxidising agent such as nitric acid is contemplated. Before using strong oxidising agents in contact with Ion Exchange Resins, consult sources knowledgeable in the handling of these materials.

Rohm and Haas Company makes no warranties either expressed or implied as to the accuracy or appropriateness of these data and expressly excludes any liability upon Rohm and Haas arising out of its use. We recommend that the prospective users determine for themselves the suitability of Rohm and Haas materials and suggestions for any use prior to their adoption. Suggestions for uses of our products of the inclusion of descriptive material from patents and the citation of specific patents in this publication should not be understood as recommending the use of our products in violation of any patent or as permission or license to use any patents of the Rohm and Haas Company and its affiliates. Material Safety Data Sheets outlining the hazards and handling methods for our products are available on request.